

Features	Test Method	Value
Length	ISO 10545 - 2	± 0.06% ± 0.5 mm
Width		± 0.17% ± 0.5 mm
Thickness		± 5% ± 0.5 mm
Straightness of Sides		± 0.07% ≤ 0.6 mm
Squareness		± 0.12% ≤ 1.1 mm
Lateral Surface Flatness/ Warpage		+ 0.12% / - 0.06% + 1.1 mm / - 0.5 mm
Water Absorption	ISO 10545 - 3	12% < E < 18%
Breaking Strength	ISO 10545 - 4	800N
Modulus Of Rupture		19 N/mm ²
Coefficient of Expansion	ISO 10545 - 8	6.5 · 10 ⁻⁶ K ⁻¹
Thermal Resistance	ISO 10545 - 9	Resistant
Crazing Resistance	ISO 10545 - 11	Resistant
Frost Resistance	ISO 10545 - 12	Not Resistant
Resistance to Low Concentrations of Acids	ISO 10545 - 13	LA
Resistance to High Concentrations of Acids		HA
Resistance to Household Cleaning Products		A
Resistance to Staining	ISO 10545 - 14	Class 5
Reaction To Fire	EN14411:2012	A1
Low Emissions Material • Zero VOC		

According to ANSI and MIA standards, depending on the type and size of tile, it is recommended to have at least a 1/8" wide grout joint for floor tiles in order to be able to fill the grout joint full and never less than 1/16" wide. Please refer to TCNA guidelines for more on grout recommendations.

Disclaimer: DCOF wet and dry is different on every production lot and can vary. If the spec listed is over the minimum standard, it will meet the requirement.

Product Info:

- White Body Ceramic Tile
- Glossy Finish
- 10.6mm Thickness
- Rectified Edge
- V2 - Slight Shading Variation
- Frost Resistance = No

